

Technical specification



Grade	2 614 055 1	Dentalkrepp weiss + alle Farben
	2 614 055 1	Rodena Dental-Crepe+ all colours

Test method			Measure	min	max
Substance	DIN 53104	-	g/m ²	53	57
Thickness	DIN 53105 T1	-	µm	190	220
Tensile strength	DIN 53112 T1	md	N/15mm	24,3	-
Tensile strength	DIN 53112 T1	cd	N/15mm	15,4	-
Wet strength	DIN 53112 T2	md	N/15mm	7,0	-
Wet strength	DIN 53112 T2	cd	N/15mm	4,5	-
Breaking length	DIN 53112 T1	md	km	3,0	-
Breaking length	DIN 53112 T1	cd	km	1,9	-
Stretch	DIN 53112 T1	md	%	8	-
pH	online	-	-	6	8
Ash content	DIN 54370	-	%	0	1
Absolute moisture content	online	-	%	3,5	6,5
Capillary rise	DIN 53106	md	mm	40	-
Capillary rise	DIN 53106	cd	mm	45	-
Brightness (white Paper)	DIN 53145 - R457	-	%	82	90
Unigloves Order number (Mastersamples for color)	white 5181; yellow 5680; orange 5870; pink 5750; green 5310; blue 5530; violett 5920				
Dental Crepe does not comply with Standard DIN EN 868-2 ,Section 4.2.2.2.3 (water repellency)					
ISO 9001; ISO 3485; REACH					

MD=Machine Direction,CD=Cross Direction,T=Top,B=Botton

All above are typical values at conditioning atmosphere 50% and 23°C according to ISO-standards.

Averages from the produced delivery